

Epoxy

PRODUCT DESCRIPTION

A two component, solvent free chemically resistant heavy duty epoxy tank lining.

INTENDED USES

To provide corrosion protection to the internals of steel storage tanks containing a range of products, including crude oil, unleaded gasoline blends, MTBE, aviation fuels, and a selected range of aromatic and aliphatic solvents.

Capable of being used as either a single coat unreinforced system, or in conjunction with fibreglass to form a glass reinforced laminate system.

PRACTICAL INFORMATION FOR INTERLINE 910

Colour	Cream, White			
Gloss Level	Not applicable			
Volume Solids	100%			
Typical Thickness	300-600 microns (12-24 mils) when used as an unreinforced system for walls or as a laminate gel coat. 400-1,000 microns (16-40 mils) for use as a single coat on tank floors. 1,250-1,400 microns (50-56 mils) when used as a laminate with fibre glass. Thickness is dependent upon application method and specification.			
Theoretical Coverage	Unreinforced: 2.50 m ² /litre at 400 microns d.f.t and stated volume solids 100 sq.ft/US gallon at 16 mils d.f.t and stated volume solids Laminate: Thickness and coverage are dependent upon the configuration of the surface to be coated			
Practical Coverage	Allow appropriate loss factors			
Method of Application	Plural Component Airless Spray, Airless Spray, Brush, Rolle			
Drying Time	Overcoating interval with self			
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	10 hours	44 hours	44 hours	7 days
15°C (59°F)	9 hours	24 hours	24 hours	5 days
25°C (77°F)	6 hours	18 hours	18 hours	3 days
40°C (104°F)	2 hours	5 hours	5 hours	24 hours

REGULATORY DATA

Flash Point (Typical)	Part A >101°C (214°F); Part B >101°C (214°F); Mixed >101°C (214°F)	
Product Weight	1.36 kg/l (11.3 lb/gal)	
VOC	88 g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)
See Product Characteristics section for further details		

Protective Coatings

Epoxy

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2½ (ISO 8501-1:2007) or SSPC SP10. A sharp, angular surface profile of 75-100 microns (3-4 mils) is recommended.

Interline 910 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Where local VOC regulations allow, surfaces may be primed with Interline 982 to 15-25 microns (0.6-1.0 mils) dry film thickness before oxidation occurs. Alternatively, the blast standard can be maintained by use of dehumidification.

Interline 982 can hold a blast for up to 28 days in the semi-protected environment of a tank interior. If moisture is present on the surface, oxidation will occur and reblasting will be required.

Laminate Systems

Prior to application of the laminate all weld seams, lap joints, plate edges or other designated areas should be caulked using Interline 903. Please refer to Interline 910 Technical Specification for Glass Fibre Reinforced Systems.

Gel Coat Application

Prior to application of the gel coat, the entire surface to be coated should be abraded to remove any protruding fibre glass strands or other irregularities. The surface should then be vacuum cleaned.

APPLICATION

Mixing	Interline 910 must be applied in accordance with the detailed International Protective Coatings Working Procedures for the application of Tank Linings.			
	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	<ol style="list-style-type: none"> (1) Agitate Base (Part A) with a power agitator. (2) Agitate Curing Agent (Part B) with a power agitator. (3) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator. 			
Mix Ratio	2 part(s) : 1 part(s) by volume			
Working Pot Life	10°C (50°F) 60 minutes	15°C (59°F) 50 minutes	25°C (77°F) 40 minutes	40°C (104°F) 15 minutes
Plural Component Airless Spray	Suitable	Consult International Protective Coatings for specific recommendations. See Product Characteristics		
Airless Spray	Recommended	Tip range 0.53-0.66 mm (21-26 thou). Total output fluid pressure at spray tip not less than 211 kg/cm ² (3000 p.s.i.)		
Air Spray (Pressure Pot)	Not recommended			
Brush	Suitable - small areas only	Typically 150-200 microns (6.0-8.0 mils) can be achieved		
Roller	Suitable - small areas only	Typically 150-200 microns (6.0-8.0 mils) can be achieved		
Thinner	Not suitable	DO NOT THIN		
Cleaner	International GTA853 or International GTA415			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA853. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA853. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Epoxy

PRODUCT CHARACTERISTICS

The detailed Interline 910 Application Guidelines should be consulted prior to use.

When utilising Interline 910 as a glass fibre laminate system, please refer to the detailed Interline 910 Technical Specification for Glass Fibre Reinforced Systems.

Exact specification for total dry film thickness and number of coats will be dependent upon service end use requirements. Consult International Protective Coatings for specific advice regarding tank lining applications.

Apply by airless spray only. Application by other methods, e.g. brush or roller, may require more than one coat and is suggested for small areas only or initial stripe coating.

Interline 910 can be applied by standard airless spray equipment when the paint temperature is maintained above 15°C (59°F). At lower temperatures an in-line heater of a suitable pressure rating may be used to assist with pumping and atomisation of the product. Additionally, Interline 910 is suitable for application by plural component airless spray equipment capable of accurate proportioning, which allows more flexible application at high temperatures, especially when applying a glass reinforced laminate system.

Heavily pitted areas should be stripe coated by brush, to ensure good "wetting" of the surface.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Do not apply at steel temperatures below 10°C (50°F). The climatic conditions within the tank must be controlled to maintain a maximum relative humidity of 70% at all temperatures.

Exposure to unacceptably low temperatures and/or high humidities during or immediately after application may result in incomplete cure and surface contamination that could jeopardise subsequent intercoat adhesion.

After the last coat has cured hard, the coating system dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the average total applied system thickness and the coating system should be free of all pinholes or other holidays. Dry film thicknesses in excess of 500 microns (20 mils), can be checked using a suitable high voltage pulsating type holiday detector, set at 100 volts per 25 microns d.f.t. (100 volts per mil). Excessive voltage may produce a holiday in the coating film. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service. Consult International Protective Coatings Interline 910 Application Guidelines for detailed repair procedures.

Maximum chemical resistance is not attained until the film has completely cured. Cure is a function of temperature, humidity and film thickness. Normally films at 400 microns (16 mils) dry film thickness will exhibit full and complete cure for optimal chemical resistance in 7-10 days at 25°C (77°F). Curing times are proportionately shorter at elevated temperatures and longer at lower temperatures.

Interline 910 may not be suitable for storage of certain aqueous media at temperatures in excess of 40°C (104°F). Consult International Protective Coatings for specific recommendations.

This material is recommended for the storage of aviation fuel. It is also suitable for storage of unleaded gasoline, although alcohol containing blends may be detrimental.

This product has the following specification approvals:

- Spanish Norma INTA 164402-A.
- Swedish Approval according to SÄIFS 1997:9 for the internal lining of steel tanks containing petrol (leaded and unleaded), paraffin oil, diesel oil and petroleum based solvents with maximum 50% aromatic content.

Note: VOC values quoted are based on maximum possible for the product taking into account variations due to colour differences and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

Interline 910 can be applied directly to correctly prepared bare steel. However, it is suitable for application over the following primer:

Interline 982

This product can also be applied over Interline 903 caulk where this material has been specified.

Interline 910 should only be topcoated with itself, and should never be overcoated with another product.

Consult International Protective Coatings to confirm that Interline 910 is suitable for contact with the product to be stored.

Epoxy

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interline 910 Application Guidelines
- Interline 910 Technical Specification for Glass Fibre Reinforced Systems

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations. All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Parts A and B if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitisation if not used correctly.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 litre	13.33 litre	20 litre	6.67 litre	10 litre
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
	20 litre	20.6 kg		9 kg	
STORAGE	Shelf Life	18 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 26/05/2016.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

SKE Beschichtungssysteme GmbH | Buchenring 11 | D-21272 Egestorf
 Fon +49 (0) 4175 / 808 99 -31 | Fax +49 (0) 4175 / 808 99 -32
 E-Mail: info@ske-beschichtungen.de | www.ske-beschichtungen.de